



AGH UNIVERSITY OF SCIENCE AND TECHNOLOGY

Faculty of Materials Science and Ceramics

Department of Building Materials Technology

WIMiC/ktmb//2014


Cracow, Dec 11, 2014

Thermal conductivity of BAUWER Light insulating plasters

REPORT

Customer: BAUWER sp. z o.o. (Ltd.)
Dojazd Staroniwa street 9/19
35-011 Rzeszów, POLAND

Samples collection date: 6.10.2014
Start of tests: 1.12.2014
End of tests: 10.12.2014



AGH UNIVERSITY OF SCIENCE AND TECHNOLOGY | Faculty of Materials Science and Ceramics
Department of Building Materials Technology

al. A. Mickiewicza 30, 30-059 Krakow, Poland, phone +48 12 617 24 52, +48 12 617 25 41, fax +48 12 617 24 52
Bank: Bank Pekao S.A. O/K`rakow, ul. Pijarska 1
Account No. 96 1240 4722 1111 0000 4858 2922
REGON: 00000 1577 NIP: 675-000-19-23

wimic

1. Aim and range of research

The test of thermal conductivity was made for BAUWER Ltd. (Rzeszów). One series of samples were investigated. Samples were marked by the customer.

2. Results

Grinded and dry rectangular samples with the dimensions 200mm×200mm×45mm were investigated. The equipment based on steady-state method according standard no. PN-ISO 8301:1998 was used. Mean temperature was 10°C, temperature gradient during tests was 10°C. Dimensions of samples comply with the criteria of standard no. PN-EN 12664:2002. The result for each sample is the mean value obtained from three particular tests.

Table 1. Thermal conductivity of samples $\lambda_{10,dry}$

No.	Samples	Density, kg/m ³	Std.dev. kg/m ³	$\lambda_{10,dry}$ W/(m·K)	Std.dev. W/(m·K)
1	Insulating plaster BAUWER Light	281	3	0,068	0,001

The results relate only to the investigated samples. Expanded uncertainty of used method for k=2 is 0,005 W/(m·K).

Waldemar Pichór, dr eng.

